



Compression of Tuff-N-Nuff

Test performed by compressing 2 layers of 3/8" x 2" x 2" Tuff-N-Nuff at a rate of 0.100 inches per minute.

Displacement	Load (lb)	Load (psi)	Compression
0.073	4.5	1.12	10%
0.147	15.5	3.89	20%
0.223	42.2	10.5	30%
0.297	94.4	23.6	40%
0.372	196.4	49.1	50%
0.447	435.8	108.1	60%